Seplife® SP HiPer 37

1. Description

Seplife® SP HiPer 37 is a strong cation exchanger agarose resin suitable for intermediate and polishing steps in proteins and mAbs downstream processing.

- High stability to CIP (cleaning in place) up to 1M NaOH.
- Hydrophilic base matrix ensures low levels of non-specific adsorption and high recovery rate.
- Regulatory Support File (RSF) is available for Seplife® SP HiPer 37.

Seplife® SP HiPer 37 is based on highly cross-linked agarose and has a particle size suitable for high capacity and high-resolution applications (30-50 micron).

2. Properties

Product	Seplife® SP HiPer 37
Appearance	White to light yellow beads
Type	Strong acid cation - Sulfopropyl
Matrix	Cross-linked 6% agarose
Ion exchange capacity (mmol/ml)	0.18-0.25 (H^+)
pH ligand fully charged	Negatively charged at pH>2.5
Particle size range (μm)	30-50
pH stability	4-13 (operational), 3-14 (CIP)
Chemical Stability	Stable in all common aqueous buffers; 1M sodium hydroxide; 8MUrea; 6M guanidine hydrochloride; 30% isopropyl alcohol; 70% ethanol;
Flow rate* (cm/h)	＞120
10% Dynamic binding capacity (mg/ml)**	≥100.0
Shipped as	Slurry in 20% ethanol solution containing 0.2M sodium acetate

*Testing conditions: Chromatography column 26mm×300mm; column bed height 20cm; 0.2MPa; temperature 25° C; mobile phase water.

** Testing conditions: Binding buffer: 20mM NaAC-HAC, pH 5.0; Elution buffer: 20mM NaAC-HAC+1M NaCl, pH 5.0; Sample: Lysozyme. Column 8mm*100mm, room temperature, Retention time 4 minutes.

3. Storage

Sealed and stored at 4-30°C (preservation solution is 20% ethanol in 0.2M sodium acetate) in a ventilated, dry and clean place, do not freeze.

4. Transportation

Avoid sunlight, rain, and crushing during transportation. It is strictly forbidden to transport together with toxic and hazardous materials.

5. Ordering information

Product Name	Product Code	Pack Size
Seplife® SP HiPer 37	A2170402	25ml
	A2170403	100ml
	A2170404	500ml
	A2170405	1L
	A2170406	5L
	A2170407	10L

Production date: See label
Expiry Date: 5 years, under proper storage conditions

Manufacturer: Sunresin New Materials Co. Ltd.
Address: No. 135, Jinye Rd, Xi'an Hi-tech Industrial Development Zone, Shaanxi, 710076, China
www.sunresinlifesciences.com
E-mail: info.lifescience@sunresin.com

All information set forth herein is for informational purposes only. This information is general descriptive(introductory) information of SUNRESIN and its related products, technologies and services. Neither shall constitute the guarantee of SUNRESIN and its affiliates to products, technologies and services in specific fields and specific application conditions results, unless otherwise expressly noted. SUNRESIN and its affiliates assumes no obligation or liability for the information in this document. Customer is responsible for judging whether the information is appropriate for Customer's concrete demand and are obliged to understand whether the use of these products, technologies and services is permitted by the laws and regulations of their countries and relevant regions. Unless expressly stated, no freedom from infringement of use any patent or trademark or intellectual property rights owned by SUNRESIN or its affiliated companies under this document is to be inferred.